



PRODUCT DATA : FAÇADES SUPERFLEXIBLE WATERPROOFING

Flexible elastic paint , specially recommended for façades waterproofing. Provides excellent flexibility and adhesion, prevents cracks due to its resistance to expansion-contraction of the support and avoids UV degradation.

Product	Façades Superflexible Waterproofing Paint
Application	Interior and exterior use
Tools	Brush and Roller
Colour	White and red.
Finish	Matte
Properties	Waterproofing paint specially recommended for façades.
Thinner	Water
Drying time	Dry to touch 2 hours. Over-coating time: 24 hours.
Spread Rate	4-6 m ² /litre.

We assume no liability if the result is affected by factors beyond our control. The user should check that the product supplied fits the needs for which it is intended and must perform a preliminary test if necessary. The information contained in this form should be used like a guide but not like a warranty. For more information in relation to safety and environment, see data safety sheet of the product

DESCRIPTION:

Flexible elastic paint , specially recommended for façades waterproofing. Provides excellent flexibility and adhesion, prevents cracks due to its resistance to expansion-contraction of the support and avoids UV degradation.

APPLICATION

Product suitable for waterproofing façades.

TECHNICAL

CHARACTERISTICS:

Vehicle: styrene acrylic copolymer

Density: 1.22 kg/l.

Viscosity: 130 KU

Drying time: dry to touch 2 hours

Over-coating : 48 hours UNE 48-086-64.

VOC EU limit value for the product (cat. A/a): 75 g/l (2007) - 30 g/l (2010)

Max. VOC content: 20 gl

Theoretical Spread rate*4-6 m²/l.

Thickness: 1.22 microns.

Tensile strength at 23°C: 1.8 MPa

Elongation at break at 23 ° C: 300 %

Bending at 5 ° C: Satisfactory

Impact resistance ,drop height 200mm : Satisfactory .

* The coverage depends on the type and condition of the surface, on the absorption of the surface as well as the mode of application and the degree of dilution.

PRODUCT DATA: FAÇADES SUPERFLEXIBLE WATERPROOFING

INSTRUCTIONS:

It can be applied by brush, roller or paint sprayer in all types of traditional paraments used in new construction or old repairs of concrete or fiber cement

Method of application:

Apply a coat of WATERPROOFER diluted with 15 to 20% water.

After a few hours and when the first coat is dry, take into account the environmental conditions, apply a second coat of ready-to-use FAÇADES SUPERFLEXIBLE WATERPROOFING , let dry and, to finish, apply a third crossed layer to ensure the coverage of the support.

The application will be completed when the thickness of the applied waterproof corresponds to 2-2.5 kg / m² To give greater strength to the breakage of FAÇADES SUPERFLEXIBLE WATERPROOFING film, a mesh can be incorporated into the layers for greater reinforcement.

CAUTIONS:

Do not apply under 5°C or over 40°C in the sun.Keep containers out of direct radiation. Keep out of reach of children.



PACKAGING

750 ml	1kg
4l	5kg
8l	10kg
14l	18kg