



## **PRODUCT DATA : ROUGH COATING R.303**

High quality rough coating stone structure. This type of coating can produce different types of long lasting finishes. Good adhesion and alkali resistance.

Product	Rough Coating R.303
Application	Interior and exterior use
Tools	Brush and Roller
Colour	White
Finish	Matte
Properties	Resistance , whiteness and covering power.
Thinner	Water
Drying time	Dry to touch 30 minutes. Over-coating time: 60 minutes.
Spread Rate	2-4 m <sup>2</sup> /litre.

We assume no liability if the result is affected by factors beyond our control. The user should check that the product supplied fits the needs for which it is intended and must perform a preliminary test if necessary. The information contained in this form should be used like a guide but not like a warranty. For more information in relation to safety and environment, see data safety sheet of the product

# PRODUCT DATA : ROUGH COATING

## R.303

### DESCRIPTION:

High quality rough coating stone structure. This type of coating can produce different types of long lasting finishes. Good adhesion and alkali resistance.

### APPLICATION

Product suitable for interior and exterior walls.

### PROPERTIES:

- Excellent quality-price ratio
- Water vapour breathability
- Excellent covering power
- Washable
- Colour: white
- No splashing

### CAUTIONS:

Do not apply under 5°C or over 40°C in the sun.

Keep containers out of direct radiation. Keep out of reach of children.

### TECHNICAL CHARACTERISTICS:

Vehicle: styrene acrylic copolymer

Density: 1.7 kg/l.

Viscosity: 140 KU

Drying time: dry to touch 30 minutes.

Over-coating : 60 minutes.

VOC EU limit value for the product (cat. A/a): 75 g/l (2007) - 30 g/l (2010)

Max. VOC content: 20 g/l

Theoretical Spread rate\* 2-4 m<sup>2</sup>/l.

\* The coverage depends on the type and condition of the surface, on the absorption of the surface as well as the mode of application and the degree of dilution.

### INSTRUCTIONS:

Surfaces to be painted must be dry and free of impurities like dust, efflorescence, rust, grease, wax, etc. and primed properly. If the surfaces are already painted and they are in good condition, clean and apply a coat of paint. Homogenize well the product before application.

Paint Thinner: Water

Dilution:

-First coat: 15-20 % water

-Second coat: 5-10 % water

It can be applied with a brush, roller or sprayer

Cleaning of tools: water



### PACKAGING

14 l	22 kg
8 l	12 kg
4l	5 kg